


14

(19)  **Europäisches Patentamt**
European Patent Office
Office européen des brevets



(11) **EP 0 864 689 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
16.09.1998 Bulletin 1998/38

(51) Int Cl.⁶: **D21C 3/22, C07C 50/18,**
C07C 43/11

(21) Application number: **98400568.6**

(22) Date of filing: **11.03.1998**

(84) Designated Contracting States:
AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(71) Applicant: **WESTVACO CORPORATION**
New York New York 10171 (US)

(72) Inventor: **Turner, William T.**
Lakeland, Florida 33813 (US)

(30) Priority: **11.03.1997 US 814375**
11.03.1997 US 814680

(74) Representative: **Portal, Gérard et al**
Cabinet Beau de Loménie
158, rue de l'Université
75340 Paris Cédex 07 (FR)

(54) **Additive composition and process for reducing anthraquinone requirements in pulping of lignocellulosic material**

(57) An improved preliminary aid composition and process for delignification of lignocellulosic raw material, such as wood chips, for the production of cellulose pulps for use in the manufacture of paper or paperboard are disclosed wherein the wood chips are treated in a closed reaction vessel with an alkaline pulping liquor with an amount of a cyclic keto compound, such as anthraquinone, included therein for achievement of a de-

termined pulp yield, wherein the improvement comprises a reduction in the amount of anthraquinone required to achieve said yield by the addition to said alkaline pulping liquor, in addition to a reduced amount of the anthraquinone, a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid.

EP 0 864 689 A2

Description

BACKGROUND OF THE INVENTION**1. Field of the Invention.**

This invention relates to an improved additive composition and process for the delignification of lignocellulosic material, such as wood, with an alkaline pulping liquor of the kraft, or sulfate, alkaline pulping process. More particularly, the invention relates to lignocellulosic material delignification with kraft pulping liquors containing a cyclic keto compound (preferably, anthraquinone), permitting enhanced yield. Specifically, the invention relates to an improvement of said additive composition and process wherein said enhanced yield is achieved at reduced anthraquinone levels via the inclusion of a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid.

2. Description of the Prior Art

In the mid-1970s, a significant advance was made in the delignification of lignocellulosic material for the production of wood pulps upon the discovery of the benefits of using anthraquinone as a pulping additive to alkaline pulping liquors. Among the earliest public disclosures of such use of anthraquinone was U.S. Patent No. 3,888,727, which taught treating lignocellulosic material with an alkaline pulping liquor containing anthraquinone sulfonic acid followed by oxygen delignification. More significantly, however, U.S. Patent No. 4,012,280 taught that the poorer economics of the environmentally preferable soda pulping process could be improved to compete with the more environmentally offensive (in terms of odor) kraft process by incorporation of anthraquinone as a pulping additive. Although the benefits of increased yield of cellulosic pulp and increased rate of delignification (permitting lower energy consumption and higher throughput) were shown, the use of the improved, lower pollution potential soda process was not advanced. First, incorporating the relatively expensive anthraquinone in the soda process to make it productively competitive with the kraft process without anthraquinone reduced its economic competitiveness. Second, the benefits of anthraquinone also were achieved in other (already more commercially employed) pulping process such as those employing kraft or polysulfide pulping liquors.

It was soon discovered, as disclosed in U.S. Patent No. 4,213,821, that anthraquinone also benefitted cooking wood chips in neutral sulfate pulping liquor (with a special case disclosed in U.S. Patent No. 5,139,617), as well as in the alkaline pulping liquors. Methods for maximizing the benefits of anthraquinone were disclosed in U.S. Patent Nos.: 4,127,439; 4,178,861; and 4,310,383. Also, due to anthraquinone's difficult-to-handle, water-insoluble, fine powder form, discoveries made to facilitate its dispersion in the pulping liquors are disclosed in U.S. Patent Nos.: 4,248,663; 4,384,921; and 4,574,032. One disadvantage to anthraquinone use is its tendency to cause scaling problems in the cooking vessel. Methods to overcome this problem are disclosed in U.S. Patent Nos.: 4,481,073 and 4,561,935. Finally, as a result of the relative high cost of anthraquinone, methods for recovering and reuse of the chemical are disclosed in U.S. Patent Nos.: 4,197,168 and 4,310,383.

In spite of the aforementioned advances, there remains a need to improve the benefits of anthraquinone pulping (primarily reduction of energy and chemical requirements while improving yield) and to reduce its disadvantages (primarily cost and equipment scaling). One approach would be to replace a portion of the anthraquinone with an additive which provided some of the benefits of anthraquinone without providing the disadvantages which accompany its use.

Therefore, an object of this invention is to provide an improved pulping additive composition and process for delignification of a lignocellulosic raw material with a pulping liquor with a cyclic keto compound, such as anthraquinone, for the production of a predetermined yield of cellulose pulp which composition and process permit the achievement of said yield, as well as other aforementioned benefits, with a reduced requirement of cyclic keto compound, such as anthraquinone, of at least 10%, and advantageously up to 50%.

SUMMARY OF THE INVENTION

The above stated object is provided by the instant invention according to a first aspect by an improved wood pulping aid composition comprising a cyclic keto compound for addition to pulping liquors in the delignification of lignocellulosic raw material characterized in that it comprises the addition of a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid.

According to a second aspect, the invention provides an improved process for the delignification of lignocellulosic raw material in the production of cellulose pulps suitable for use in the manufacture of paper or paperboard comprising treating the lignocellulosic raw material in a closed reaction vessel with an alkaline pulping liquor with an amount of a

cyclic keto compound included therein to achieve a determined pulp yield, characterized in that it comprises providing a reduction in the amount of the cyclic keto compound required to achieve said yield by adding to said alkaline pulping liquor a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid.

Also, according to a third aspect, the present invention relates to the use of a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and a 12-hydroxystearic acid as an additive to an alkaline pulping liquor, preferably in combination with a cyclic keto compound.

Advantageous embodiments of the invention according to any of the above aspects are set forth in the sub-claims which are incorporated in the specification in full by reference.

DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

The improved process of this invention comprises the steps of (1) treating lignocellulosic material in a closed reaction vessel with an alkaline pulping liquor containing a cyclic keto compound additive selected from the group consisting of naphthoquinone, anthraquinone, en throne, phenanthrenequinone, the alkyl, alkoxy, and amino derivatives of said quinones, 6,11-dioxo-1H-anthra [1,2-c]pyrazole, anthraquinone-1,2-naphthacrinone, 7,12-dioxo-7,12-dihydroanthra[1,2-b]pyrazine, 1,2-benzanthraquinone, and 10-methylene en throne, the treatment taking place at a maximum temperature of from about 150° to about 200°C for a period from about 0.5 to about 480 minutes to achieve a determined pulp yield, and (2) displacing the pulping liquor from the lignocellulosic material with water or an aqueous liquor inert to the lignocellulosic material to obtain a determined yield of a delignified cellulosic material, wherein the improvement comprises a reduction in the amount of cyclic keto compound additive required to achieve said yield by the addition to the alkaline pulping liquor, in addition to a reduced amount of the cyclic keto compound, a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid.

The delignified cellulosic material produced by the above two steps may be used without further treatment or may be subjected to conventional bleaching steps.

When the lignocellulosic material to be treated is wood, it is first converted into the form of chips. This step is not required when the lignocellulosic material is of fibrous form.

The lignocellulosic material may be refined between steps (1) and (2). Refining can be carried out with known equipment, such as a single disc or double disc refiner.

The process of this invention may be used to delignify either coniferous or deciduous species of wood. By coniferous is meant species such as pine, spruce, and balsam fir. By deciduous is meant species such as birch, aspen, eastern cottonwood, maple, beech, and oak.

The alkyl alcohol alkoxylate component of the surfactant mixture is preferably a C₄-C₃₀ alkyl alcohol alkoxylate prepared by reacting an alcohol, which may have either a linear or branched chain and may be either a primary or secondary alcohol, with from about 5 moles to about 100 moles of an alkylene oxide selected from the group of ethylene oxide, propylene oxide, butylene oxide, and any combination thereof. A particular preferred alkyl alcohol alkoxylate is oleyl alcohol ethoxylate prepared with 23 moles ethylene oxide.

The member of the group of polyoxyalkylene glycol ethers of an ester of an acid selected from the group of ricinoleic acid and hydroxy stearic acid can be prepared by reacting an ester of a glycol, selected from the group of glycerine, neopentyl glycol, trimethylethane, trimethylolpropane, pentaerythritol and its polymers, mannitol, and sorbitol, with from about 5 moles to about 100 moles of an alkylene oxide selected from the group of ethylene oxide, propylene oxide, butylene oxide, and any combination thereof. Inasmuch as ricinoleic acid is the primary component (~90%) of castor oil, although present as a triglyceride rather than in free acid form, castor oil may be alkoxylated directly to form the required polyoxyalkylene glycol ethers of the esters of ricinoleic acid. Therefore, a preferred member of this group is ricinoleic acid triglyceride ethoxylate.

U.S. Patent Nos. 5,298,120 and 5,501,769 disclose pulping wood using fatty acid esters of polyoxyalkylene glycols to enhance pulping uniformity and pulp yield. While these esters may give the desired performance, there is an inherent weakness in the molecule when used in strongly alkaline solutions which are heated to high temperatures. The ester will cleave and form both a fatty acid soap and the polyalkylene glycol used to form the ester. Thus, it ceases to be the ester claimed. Also, the beneficial results are not being produced by the disclosed compound, rather the beneficial results are, in fact, diminished by the products of this cleavage.

This is not the case with the claimed alkyl alcohol polyalkylene glycol ethers and the polyalkylene glycol ether of ricinoleic acid triglyceride (of castor oil), which can give superior performance in the strong, hot alkaline solutions used in pulping wood. When the ester of the polyalkylene glycol ether of ricinoleic acid triglyceride cleaves, the resultant molecule will be the sodium salt of polyalkylene glycol ether of ricinoleic acid, which is a surfactant and which will have functionality in the pulping solution. The presence of the sodium salt of the polyalkylene glycol ether of ricinoleic acid

will assist in solubilizing the alkyl alcohol polyalkylene glycol ethers in the hot, alkaline pulping solution as the pulping process is completed. The solubilization of the other surfactants is of great benefit since, otherwise, these other surfactants may precipitate out of solution and be of less benefit.

The composition of the invention is preferably a microemulsion prepared by combining an oleyl alcohol ethoxylate with a ricinoleic acid triglyceride ethoxylate in a weight ratio of from about 4:1 to about 1:4 (preferably, about 1:2), respectively. For combination with anthraquinone for use in alkaline pulping, an aqueous solution of the composition is prepared by blending with from about 10 to about 30% (preferably, about 20%) water, producing a clear viscous solution. This solution is, in turn, diluted with water to form about 10 to about 30% (preferably, about 12.5%) active when combined with the aqueous dispersion of anthraquinone. The invention surfactant composition should exhibit an HLB of from about 5 to about 20 preferably from about 8 to about 16. Upon combination of the components of the surfactant composition, a microemulsion is formed which exhibits an average particle size of from about 0.5 to about 10 μm , preferably from about 1 to about 4 μm and most preferably less than 2 μm .

Evidence that a microemulsion of the proper average particle size to accomplish the observed synergism with anthraquinone has been formed is that, upon combination of the two components at ambient temperature, a transparent solution is formed, and, upon heating to about 82°C (180°F), the solution turns a hazy bluish color.

The cyclic keto compound, preferably anthraquinone, is preferably prepared as an aqueous dispersion which is combined with the invention surfactant compound prior to their addition to the cooking vessel. The anthraquinone dispersion is preferably prepared by the addition of a dispersant and by reducing the anthraquinone average particle size to from about 6 to about 10 μm in water by wet grinding or milling. A preferred dispersant may be a sodium lignosulfonate.

Although the surfactant composition and the anthraquinone dispersion may be added separately to the cooking vessel, it is preferred that they be combined prior to such addition and then added as a single aqueous blend. The surfactant microemulsion serves to coat the anthraquinone particles and allows the mixture of anthraquinone and pulping liquors to penetrate the wood chips at a faster rate and saturate them more efficiently and completely. It is envisioned that it is this mechanism which results in obtaining the desired kappa number and lower rejects using significantly less anthraquinone.

The benefits of the invention process and composition are seen in the following examples.

Example 1

For comparison purposes, 59,090 kg (sixty-five wet tons) of conifer wood chips were loaded into a pulping digester filled with kraft alkaline pulping liquors providing an average of about 4,909 kg (about 10,800 pounds) active alkali a liquor to wood ratio of about 3.45, after which 22.7 kg (50 wet pounds) of a 50% anthraquinone dispersion (0.08% by weight, based on the weight of oven dried wood chips) were added. The digester contents were heated up to a maximum temperature of 166°C (332°F) and the wood chips were cooked for 79 minutes to a kappa number of 91. The cook resulted in a yield of 54%, and rejects of 10%.

Example 2

For use as an additional digestion aid to enhance the benefits of anthraquinone, several samples of the invention surfactant were prepared and evaluated for microemulsion performance. In varying proportions, an oleyl alcohol ethoxylate prepared with 23 moles ethylene oxide was combined with a ricinoleic acid triglyceride ethoxylate and water. In each case, upon blending the components together, a clear, viscous solution was formed.

Sample A:	
oleyl alcohol ethoxylate - 23 moles EO	20 parts by weight
ricinoleic acid triglyceride ethoxylate	60 parts by weight
water	20 parts by weight
Sample B:	
oleyl alcohol ethoxylate - 23 moles EO	40 parts by weight
ricinoleic acid triglyceride ethoxylate	40 parts by weight
water	20 parts by weight
Sample C:	
oleyl alcohol ethoxylate - 23 moles EO	60 parts by weight

(continued)

Sample C:	
ricinoleic acid triglyceride ethoxylate	20 parts by weight
water	20 parts by weight

Each sample was diluted to 12.5 wt% with water and heated to 82°C (180°F). At ambient temperature all diluted samples gave transparent solutions, and at 82°C (180°F) each sample turned a hazy bluish color.

Example 3

The process of Example 1 was again conducted; except, in place of the 0.08% anthraquinone, 0.06% by weight based on oven dried wood chips of a digestion aid comprised of the surfactant blend of Sample A from Example 2 and anthraquinone was added to the white liquor as the white liquor was simultaneously pumped into the digester while the wood chips were being added. Upon completion of the digestion cycle, a pulp having a kappa number of 90 was produced with rejects of under 10%.

Compared with the performance of anthraquinone alone in Example 1, it is noted that a reduction by 25% of digestion aid (using the invention pulping additive) gave a lower kappa number and a significantly lower reject level. Moreover, when a comparison is made based on the respective anthraquinone content of the respective digestion aids, a reduction in anthraquinone required of at least 50% is permitted by the invention surfactant composition.

Other advantages of using a digestion aid having less anthraquinone include:

1. Less tendency for formation of scale on the evaporator tubes and plugging of the tubes; and
2. Reduced contamination of the crude tall oil, which lessens problems in the tall oil refinery and reduces contamination of the tall oil heads fraction.

While the invention has been described and illustrated herein by references to various specific materials, procedures, and examples, it is understood that the invention is not restricted to the particular materials, combinations of materials, and procedures selected for that purpose. Numerous variations of such details can be employed, as will be appreciated by those skilled in the art.

Claims

1. An improved wood pulping aid composition comprising a cyclic keto compound for addition to pulping liquors in the delignification of lignocellulosic raw material characterized in that it comprises the addition of a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid.
2. The improved composition of claim 1 wherein the alkyl alcohol alkoxylates are prepared by reacting one or more C₄-C₃₀ alkyl alcohols with a member of the group of oxides consisting of ethylene oxide, propylene oxide, butylene oxide, and any combination thereof.
3. The improved composition of claim 2 wherein the C₄-C₃₀ alkyl alcohols are derived from coconut oil, palm kernel oil, and petroleum.
4. The improved composition of any one of claims 1 to 3, wherein the polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and hydroxy stearic acid is prepared by reacting an ester of a glycol selected from the group consisting of glycerine, neopentyl glycol, trimethylolethane, trimethylolpropane, pentaerythritol and its polymers, mannitol, and sorbitol, with from about 5 moles to about 100 moles of an alkylene oxide selected from the group of ethylene oxide, propylene oxide, butylene oxide, and any combination thereof.
5. The improved composition of any one of claims 1 to 4, wherein the reduction in the amount of the cyclic keto compound required is up to 50%.
6. The improved composition of any one of claims 1 to 5, wherein the reduction in the amount of the cyclic keto compound required is up to 25%.

7. The improved composition of any one of claims 1 to 6, wherein the cyclic keto compound is selected from the group of compounds consisting of naphthoquinone, anthraquinone, anthrone, phenanthrenequinone, the alkyl, alkoxy, and amino derivatives of said quinones, 6,11-dioxo-1H-anthra [1,2-c]pyrazole, anthraquinone-1,2-naphthacridone, 7,12-dioxo-7,12-dihydroanthra[1,2-b]pyrazine, 1,2-benzanthraquinone, and 10-methylene anthrone.
8. The improved composition of any one of claims 1 to 7, wherein the cyclic keto compound and the surfactant mixture are introduced to the alkaline pulping liquor simultaneously via an aqueous blend in a ratio of from 10:1 to 1:10, respectively.
9. The improved composition of any one of claims 2 to 8, wherein the C₄-C₃₀ alkyl alcohols are selected from the group consisting of primary alcohols and secondary alcohols having a linear or branched chain, and a combination thereof.
10. The improved composition of any one of claims 2 to 9, wherein the member is reacted in an amount of from 5 to 100 moles.
11. The improved composition of any one of claims 2 to 10, wherein the member is ethylene oxide.
12. The improved composition of any one of claims 1 to 11, wherein the alkaline pulping liquor comprises sodium hydroxide, sodium carbonate, and sodium sulfide.
13. An improved process for the delignification of lignocellulosic raw material in the production of cellulose pulps suitable for use in the manufacture of paper or paperboard comprising treating the lignocellulosic raw material in a closed reaction vessel with an alkaline pulping liquor with an amount of a cyclic keto compound included therein to achieve a determined pulp yield, characterized in that it comprises providing a reduction in the amount of the cyclic keto compound required to achieve said yield by adding to said alkaline pulping liquor a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid.
14. The improved process of claim 13 wherein the alkyl alcohol alkoxylates are prepared by reacting one or more C₄-C₃₀ alkyl alcohols with a member of the group of oxides consisting of ethylene oxide, propylene oxide, butylene oxide, and any combination thereof.
15. The improved process of claims 13 or 14, wherein the C₄-C₃₀ alkyl alcohols are derived from coconut oil, palm kernel oil, and petroleum.
16. The improved process of claim 13 wherein the polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid is prepared by reacting an ester of a glycol selected from the group consisting of glycerine, neopentyl glycol, trimethylolethane, trimethylolpropane, pentaerythritol and its polymers, mannitol, and sorbitol, with from about 5 moles to about 100 moles of an alkylene oxide selected from the group of ethylene oxide, propylene oxide, butylene oxide, and any combination thereof.
17. The improved process of any one of claims 13 to 16, wherein the reduction in the amount of the cyclic keto compound required is up to 50%.
18. The improved process of any one of claims 13 to 17, wherein the reduction in the amount of the cyclic keto compound required is up to 25%.
19. The improved process of any one of claims 13 to 18, wherein the cyclic keto compound is selected from the group of compounds consisting of naphthoquinone, anthraquinone, anthrone, phenanthrenequinone, the alkyl, alkoxy, and amino derivatives of said quinones, 6,11-dioxo-1H-anthra [1,2-c]pyrazole, anthraquinone-1,2-naphthacridone, 7,12-dioxo-7,12-dihydroanthra[1,2-b]pyrazine, 1,2-benzanthraquinone, and 10-methylene anthrone.
20. The improved process of any one of claims 13 to 19, wherein the cyclic keto compound and the surfactant mixture are introduced to the alkaline pulping liquor simultaneously via an aqueous blend in a ratio of from 10:1 to 1:10, respectively.
21. The improved process of any one of claims 14 to 20, wherein the C₄-C₃₀ alkyl alcohols are selected from the group

consisting of primary alcohols and secondary alcohols having a linear or branched chain, and a combination thereof.

22. The improved process of any one of claims 14 to 21, wherein the member is reacted in an amount of from 5 to 100 moles.

23. The improved process of any one of claims 14 to 22, wherein the member is ethylene oxide.

24. The improved process of any one of claims 13 to 23, wherein the alkaline pulping liquor comprises sodium hydroxide, sodium carbonate, and sodium sulfide.

25. Use of a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid as an additive to an alkaline pulping liquor, preferably in combination with a cyclic keto compound to reduce the amount required of said cyclic keto compound, preferably, said surfactant mixture and said cyclic keto compound are as defined in any one of claims 1 to 11 and said alkaline pulping liquor is as defined in claim 12.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 864 689 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
16.06.1999 Bulletin 1999/24

(51) Int Cl.⁶: **D21C 3/22, C07C 50/18,
C07C 43/11**

(43) Date of publication A2:
16.09.1998 Bulletin 1998/38

(21) Application number: **98400568.6**

(22) Date of filing: **11.03.1998**

(84) Designated Contracting States:
**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(71) Applicant: **WESTVACO CORPORATION**
New York New York 10171 (US)

(72) Inventor: **Turner, William T.**
Lakeland, Florida 33813 (US)

(30) Priority: **11.03.1997 US 814375**
11.03.1997 US 814680

(74) Representative: **Portal, Gérard et al**
Cabinet Beau de Loménie
158, rue de l'Université
75340 Paris Cédex 07 (FR)

(54) **Additive composition and process for reducing anthraquinone requirements in pulping of lignocellulosic material**

(57) An improved preliminary aid composition and process for delignification of lignocellulosic raw material, such as wood chips, for the production of cellulose pulps for use in the manufacture of paper or paperboard are disclosed wherein the wood chips are treated in a closed reaction vessel with an alkaline pulping liquor with an amount of a cyclic keto compound, such as anthraquinone, included therein for achievement of a de-

termined pulp yield, wherein the improvement comprises a reduction in the amount of anthraquinone required to achieve said yield by the addition to said alkaline pulping liquor, in addition to a reduced amount of the anthraquinone, a surfactant mixture comprising at least one alkyl alcohol alkoxylate and at least one polyoxyalkylene glycol ether of an ester of an acid selected from the group consisting of ricinoleic acid and 12-hydroxystearic acid.

EP 0 864 689 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 40 0568

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A,D	US 5 298 120 A (BLACKSTONE MICHAEL) 29 March 1994 * column 4, line 36 - column 5, line 6 * ---	1-25	D21C3/22 C07C50/18 C07C43/11
A	US 5 032 224 A (AHLUWALIA MADHU R) 16 July 1991 * column 3, line 50 - column 5, line 15 * ---	1-25	
A,D	US 4 481 073 A (SAKAI KAZUAKI ET AL) 6 November 1984 * column 4, line 60 - column 5, line 8 * ---	1-25	
A	DATABASE WPI Section Ch, Week 8204 Derwent Publications Ltd., London, GB; Class A97, AN 82-06736E XP002100591 & JP 56 161345 A (NIPPON JORYU KOGYO KK) , 11 December 1981 * abstract * ---	1-25	
A	DATABASE WPI Section Ch, Week 9410 Derwent Publications Ltd., London, GB; Class A97, AN 94-080431 XP002100592 & JP 06 033386 A (NIPPON JORYU KOGYO KK) , 8 February 1994 * abstract * -----	1-25	TECHNICAL FIELDS SEARCHED (Int.Cl.6) D21C C07C
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 20 April 1999	Examiner Naeslund, P
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention E: earlier patent document, not published on, or after the filing date D: document cited in the application L: document cited for other reasons A: member of the same patent family, corresponding document			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 40 0568

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on the European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

20-04-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5298120 A	29-03-1994	CA 2112771 A	05-07-1995
		US 5501769 A	26-03-1996
US 5032224 A	16-07-1991	AU 620242 B	13-02-1992
		AU 5404190 A	22-10-1990
		CA 2049360 A, C	28-09-1990
		EP 0465579 A	15-01-1992
		NO 177937 B	11-09-1995
		RU 2042002 C	20-08-1995
		WO 9011401 A	04-10-1990
US 4481073 A	06-11-1984	JP 57091797 A	08-06-1982
		JP 1471436 C	14-12-1988
		JP 57100199 A	22-06-1982
		JP 63013477 B	25-03-1988
		AU 551081 B	17-04-1986
		AU 7762881 A	10-06-1982
		BR 8107787 A	31-08-1982
		CA 1182723 A	19-02-1985
		FI 813798 A	02-06-1982
		FR 2495193 A	04-06-1982
		SE 454362 B	25-04-1988
		SE 8107137 A	02-06-1982
		US 4561935 A	31-12-1985

EP 0 864 689 A3

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82